

DETAILS


Company Name:	Giatec Scientific
Project Name:	High- Rise Building
Section Name:	Wall- Level 2
Sensor Name:	Surface vs. core
Tagged By:	Project Manager Joy
Pouring Time:	2020-09-01 07:07:27
Concrete Mix:	5000 psi
Threshold:	75% of specified strength (3807 PSI)




TEST RESULTS

	Cable	Body
Max Temperature:	126.88 °F	112.5 °F
Min Temperature:	62.35 °F	66.58 °F
Maturity Index:	10956.28 °F-hrs	9099.62 °F-hrs
Strength:	5254.56 psi	4999.01 psi

TEMPERATURE



MATURITY



STRENGTH

